

National Exams December 2013

**07-Mec-B8** Engineering Materials

3 Hours Duration

NOTES:

1. If doubts exist as to the interpretation of any question, the candidate is urged to submit with the answer paper, a clear statement of any assumptions made.
2. Any non-communicating calculator is permitted. This is an open book exam.
3. Any FIVE (5) questions constitute a complete exam paper. If more than five questions are attempted, only the first five as they appear in the answer book will be marked.
4. All problems are of equal value.

1- Describe the heat treatment scheme that would provide the following property changes to 1080 steel: (refer your treatments to the appropriate time-temperature-transformation curve)

- a- Pearlite to bainite
  - b- Martensite to fine pearlite
  - c- Pearlite to martensite
  - d- 100% pearlite to a mixture of 50% pearlite and 50% martensite
  - e- Mixture of 75% pearlite and 25% martensite to 100% tempered martensite
- 

2- A polymer has an average molecular weight of 6250 and a degree of polymerization (DP) of 100. Determine whether the polymer is polyvinyl chloride or polypropylene, given the following elements atomic weights: H: 1.01 amu, C: 12.01 amu, Cl: 35.45 amu.

---

3- A ductile metal wire of uniform cross-section is loaded in tension until it just begins to neck. The curve of true stress  $\sigma$  vs. true strain  $\epsilon$  for this wire approximates to:

$$\sigma = 310 \epsilon^{0.40} \text{ MPa}$$

- a- Assuming that the volume is conserved, derive a differential equation relating the true stress to the true strain at the point of necking.
  - b- Estimate the ultimate tensile strength of the metal and the work required to take  $0.1 \text{ m}^3$  of the wire to necking.
- 

4- A composite made of hardened PVC plastic reinforced with E-glass fibers is being used as a structural material. Assume the modulus of elasticity of E-glass is 72 GPa and for PVC is 2.5 GPa. If the PVC constitutes 62% per volume of the composite, calculate:

- a- the modulus of elasticity of the composite,
  - b- the percentage of stress carried by the glass fibers, and
  - c- assuming that the composite has a cross-sectional area of  $500 \text{ mm}^2$  and is subjected to a longitudinal load of 75,000 N, calculate the corresponding strain.
- 

5- Floor beams of a transport airplane have been designed using an aluminum alloy containing 5 wt% Cu and 1.5 wt% Mg for a total weight of 7000 kg. A customer has ordered the airplane but requested that its total weight be reduced by 750 kg for fuel saving purposes. An engineer in the design and analysis department has suggested that the weight saving objective can be accomplished by replacing the aluminum alloy of the floor beams with an aluminum-lithium one containing 4 wt% Li and 1 wt % Cu. Is this possible? Answer the question by estimating the weight savings that will take place using the Al-Li alloy. Assume weighted averages of density and use the following densities for the mentioned materials:

$$\text{Al} = 2.70 \text{ g/cm}^3 \quad \text{Cu} = 8.92 \text{ g/cm}^3 \quad \text{Mg} = 1.74 \text{ g/cm}^3 \quad \text{Li} = 0.53 \text{ g/cm}^3$$

---

6- Advanced fiber-reinforced plastic (FRP) composites are now commonly used in aircraft manufacturing for both primary and secondary load bearing applications.

- a- Present four different processing methods that may be used to consolidate FRP laminated components for such applications and,
  - b- Discuss the main advantages and disadvantages of each method in relationship to such considerations as mechanical properties, geometrical aspects, processing speeds, cost, size, etc.
- 

7- A 0.5 kg magnesium sacrificial anode in a hot water heater is used up in 10 years.

- a- What is the anode reaction?
- b- What is the average corrosion current supplied by the anode?

Use an electromechanical valence of 2 and an atomic mass of 24.3 amu for Mg.

---

8- A barium-borate glass system ( $\text{BaO} \cdot 4\text{B}_2\text{O}_3$ ) is converted into a glass-ceramic by re-melting the glass and the addition of  $\text{TiO}_2$  as a nucleating agent to the re-melted batch. Referring to the periodic table of elements to obtain the molecular weights of each component element, calculate the composition of the new glass-ceramic in weight percent, if 10 mole%  $\text{TiO}_2$  is used for this conversion.

---